

FOLII AUTO Alpa SC Eli Custom SRL	Transmisia energiei solare	Reflexia energiei solare	Absorbția energiei solare	Transparența luminii vizibile	Reflexia luminii vizibile	Capacitatea transmisiei ultraviolete	Reflexia totală a energiei solare
AT 05 GR SR HPR	39%	7%	54%	5%	5%	<1%	45%
AT 15 GR SR HPR	54%	7%	39%	18%	5%	<1%	35%
AT 20 GR SR HPR	51%	7%	42%	22%	6%	<1%	37%
AT 35 GR SR HPR	55%	7%	38%	34%	6%	<1%	35%
AT 50 GR SR HPR	68%	7%	25%	53%	7%	<1%	26%
AT 70 GR SR HPR	75%	9%	16%	73%	8%	<1%	20%
ATRS 5 DL SR HPR	14%	30%	56%	6%	12%	<1%	70%
ATR 20 CH SR HPR	28%	18%	54%	21%	12%	<1%	56%
ATR 20 BR SR HPR	27%	16%	57%	18%	9%	<1%	56%
ATR 35 CH SR HPR	36%	19%	45%	38%	14%	<1%	51%
ATR 35 BR SR HPR	35%	17%	48%	35%	12%	<1%	51%
ATR 50 BR SR HPR	59%	8%	33%	55%	8%	<1%	34%
PD 10 GG SR HPR	36%	7%	57%	13%	6%	<1%	48%
PP 20 LU SR HPR	22%	26%	52%	24%	29%	<1%	63%
PP 35 LU SR HPR	36%	16%	48%	36%	18%	<1%	52%
PP 50 LU SR HPR	48%	12%	40%	49%	13%	<1%	40%
PP 58 LU SR HPR	58%	10%	32%	59%	11%	<1%	33%
DL 25 BL SR HPR	35%	13%	52%	32%	10%	<1%	51%
DL 30 GN SR HPR	32%	18%	50%	30%	15%	<1%	30%
AU 75 UV SR HPR	84%	9%	7%	78%	8%	<0,1%	20%
AN 20 N SR PS	27%	25%	48%	22%	25%	<1%	60%
AP 60 GN SR PS	48%	22%	30%	57%	14%	<1%	44%
SA 15 C SR PS4	44%	7%	49%	17%	5%	<1%	43%
SA 35 C SR PS4	56%	7%	37%	38%	6%	<1%	34%
SA 50 C SR PS4	62%	7%	31%	52%	6%	<1%	29%
SCL SR PS4	84%	9%	7%	89%	9%	<5%	14%