

FOLII AUTO Alpa SC Eli Custom SRL	Transmisia energiei solare	Reflexia energiei solare	Absorbția energiei solare	Transparența luminii vizibile	Reflexia luminii vizibile	Capacitatea transmisiei ultraviolete	Reflexia totală a energiei solare
R 15 B SR HPR	9%	34%	57%	8%	18%	<1%	76%
R 15 GO SR HPR	12%	55%	33%	15%	50%	<1%	78%
R 15 G SR HPR	9%	30%	61%	7%	13%	<1%	74%
R 15 BL SR HPR	18%	35%	47%	12%	18%	<1%	72%
R 20 SR HPR	12%	55%	33%	15%	60%	<1%	79%
R 30 B SR HPR	21%	22%	57%	19%	12%	<1%	63%
R 30 G SR HPR	23%	23%	54%	22%	13%	<1%	62%
R 35 SR HPR	22%	43%	35%	28%	44%	<1%	68%
R 50 SR HPR	37%	27%	36%	47%	27%	<1%	54%
R 40 SR PA	30%	33%	37%	39%	36%	<1%	60%
RR 20 PS	15%	62%	23%	19%	60%	<1%	79%
RR 20 B PS	9%	44%	47%	8%	20%	<1%	79%
RR 35 PS	23%	43%	34%	29%	45%	<1%	69%
REX 20 SI ER HPR	13%	49%	38%	16%	53%	<1%	77%
REX 35 SI ER HPR	22%	39%	39%	26%	41%	<1%	68%
REX 50 SI ER HPR	37%	33%	30%	47%	31%	<1%	55%
VE 35 SR CDF	22%	36%	42%	32%	35%	<0,1%	69%
VE 50 SR CDF	36%	31%	33%	49%	27%	<0,1%	57%
V 14 SR CDF	10%	50%	40%	12%	54%	<0,1%	78%
V 28 SR CDF	22%	33%	45%	27%	34%	<0,1%	65%
V 38 SR CDF	21%	25%	54%	37%	27%	<0,1%	56%
V 48 SR CDF	39%	17%	44%	47%	16%	<0,1%	48%